

JC20 Rec'd PCT/PTO 23 SEP 2009

METHOD OF PRODUCING A DIGITAL PRINTING INK AND PRODUCT THUS OBTAINED

Method of producing a digital printing ink and ink thus obtained characterized by including the following steps: dispersing pigments in a mixture of oligomers and monomers with a maximum particle size of 1 micron; diluting same with a mixture of monofunctional and multifunctional acrylic monomers until a viscosity of between 10 and 30 centipoises is obtained; introducing a photoinitiator system which causes the polymerization of the oligomers and monomers from the first step, in the presence of ultraviolet radiation; and subjecting the resulting ink to a filtration process.

BACKGROUND OF THE INVENTION

Different state-of-the-art procedures and ultraviolet curing inks are known for digital printing. Specifically, this refers to inks based in monofunctional monomers.

Other digital inks can be for laser printers. These inks start out with toner or powdered ink and through an electrostatic charge from the printer transfer the ink using a laser beam.

Also known are inkjet inks that use nozzles to direct the ink using previously digitized information from the computer.

Computer to Plate printing inks are also known, consisting of a previously created computer file, which will make the electronic stamping on the plates.

In fact, the vast majority of inks known to date follow the same scheme:

A sublimatable pigment or mixture of pigments to which a soluble resin is added to be used as a medium.

Then, an organic solvent is introduced (water-based or pure), or a mixture of a water-based organic solvent and a pure one.

Finally, a resin is used as a thickening agent or as adhesive for the ink.

Also, it can be noted that resins can be identical and that they can include additives like ethyl alcohol or butanol, among others.

This outline is followed by the 1973 Spanish patent No. 413.791 from CIBA-GEIGY AG, consisting of a method to prepare printing inks for printing by

transference through sublimation, where the advantage is in allowing the combination of concentrated preparations rich in pigments.

Patent USA No. 6.383.274 describes an inkjet water-based printing ink in which the printing bleeding agent includes a fluorinated composition, specifically a perfluoroalkyl acid salt. This patent underlines that the advantages of these inks are: reduction of drying time and, specially, prevention of ink bleeding.

BRIEF DESCRIPTION OF THE REQUESTED INVENTION

The present invention is an advancement in the field of ink production, particularly inks for digital printing.

Such inks, once printed on the media, are dried through radiation, which causes the polymerization of the ink, and results in an immediate fixation to the media as well as feeling dry to the touch.

This ink completely changes the concept of previously mentioned inks because it has a pigment or mixture of pigments but lacks any kind of resin used as a medium, or any organic solvent or resin that might serve as thickening agent, because its special composition makes this unnecessary.

All of this because the medium for the procedure is formed at the time of the polymerization of the monomers and oligomers.

At the same time, monomers and oligomers themselves act as solvents, thus forming the resin at the time of polymerization.

For all these reasons, the use of water or other solvents is not necessary in order to produce this ink.

SPECIFIC PROCESS FOR THE REQUESTED PATENT

Thus, the specific process for the present invention requires that in order to produce an ink-jet digital printing ink, the following steps must be completed:

For the first step, proceed to the dispersion of pigments in a mixture of oligomers and monomers, in such a way that the maximum size of the particle would not be more than 1 micron.

Such dispersion of pigments is obtained by using a high energy ball mill, combined

with the application of a constant temperature between 35°C and 80°C, milling until an average particle size between 0.1 and 0.8 microns is obtained, and combining all of the above with a mixture of polyol acrylate monomers and dispersants, in order to avoid re-agglomeration of dispersing pigments.

This is subsequently diluted with a mixture of monofunctional and multifunctional acrylic monomers until a viscosity between 10 and 30 centipoises is achieved.

Thus, regarding this monofunctional acrylic monomer, the ideal ratio is the one found between 10% and 25% of total acrylic monomers.

Of the multifunctional acrylic monomers, between 50% and 90% of total acrylic monomers, those that are bifunctional or trifunctional must be differentiated.

Among bifunctional acrylic monomers, Hexandioldiacrylate, Tripropyleneglycoldiacrylate, and Dipropylenglycoldiacrylate will be used for this specific process.

Among trifunctional acrylic monomers, etoxylated Trimethylolpropanetriacrylate will be used.

Also, this formulation uses polyol acrylates to improve humectation of the pigments.

Then, a photoinitiator system is introduced, which starts the polymerization of the oligomers and monomers from the first step, because of the liberation of radicals after being subject to ultraviolet radiation.

Later, once the ink formulation is finished, and the desired viscosity has been obtained, the resulting ink is subject to a filtration process in order to retain particles by means of successive filters ending with a 1 micron filter, retaining all those particles bigger than 1 micron.

This ink is particularly useful for printing on flexible media, such as paper, plastified elements, plastic films, etc.

Such flexible media, through drop-on-demand piezoelectric heads, also known in the industry as ink-jets, eject ink drops until the desired image or picture is formed.

Once the resulting ink has been printed on a media, a radiation source is applied on the ink, i.e. the light from an ultraviolet lamp or through electron bombing, which fracture the molecules of the photoinitiator system, turning them into free radicals that react, violently and quickly, to the oligomers and monomers, resulting in a polymer that

sets the dispersing pigments on the printed media.

The ink thus obtained has as a distinguishable advantage its high reactivity as compared with existing ones, allowing its use on absorbing media obtaining thus good curing of the ink film. This allows direct printing on such media without having to apply a coating to seal the pores.

This invention patent describes a new method of producing a digital printing ink and the ink thus obtained. The examples mentioned herein are not limited to this invention and will therefore have different applications and/or adaptations, all of them within the scope of the following claims.